



Boy Technology CO.,LTD

Aluminum-based CCL Performance Table

Item	Test condition	Unit	Indicator	AL-01-B 10	AL-01-B 15	AL-01-B 20
Thermal conductivity	ASTM D5470	W/m.K	—	1.0 W	1.5 W	2.0 W
Thermal resistivity	ASTM D5470	°C/W	—	0.75	0.64	0.55
Thermal stress	Solder dip 288°C	Minute	≥15	25	25	25
Peel strength	IPC-TM-650 2.4.8	Lb/in	≥8	9	9	9
Volume resistivity	IPC-TM-650 2.5.17	MΩ.cm	≥10 ⁶	10 ⁸	10 ⁸	10 ⁸
Surface resistivity	IPC-TM-650 2.5.17	MΩ	≥10 ⁴	10 ⁷	10 ⁷	10 ⁷
Dielectric constant	IPC-TM-650 2.5.5.3	1MHz	—	4.6	4.6	4.6
Dissipation Factor	IPC-TM-650 2.5.5.3	1MHz	—	≤0.02	≤0.02	≤0.02
Breakdown voltage	IPC-TM-650 2.5.6.2	KV	120+/- 10um	5.0 KV	5.0 KV	5.0 KV
Flammability	UL94	Class	V-0	V-0	V-0	V-0
CTI	IEC60112	v	≥600	600	600	600
TG	DSC	°C	—	110	110	110
Arc resistance	IPC-TM-650 2.5.1	S	≥60	120	120	120
TD	TGA(Wt5%loss)	°C	≥360	370	375	375
Moisture Absorption	D-24/23	%	≤1.5	0.5	0.5	0.5
	IPC-TM-650 2.6.2.1					
MOT	UL	°C	—	130	130	130
CTE(Z-axis)	IPC-TM-650 2.4.24 (Before Tg)	ppm/°C	—	15	15	15
	IPC-TM-650 2.4.24 (After Tg)	ppm/°C	—	45	45	45
	IPC-TM-650 2.4.24 (50- 260°C)	%	—	0.5	0.5	0.5

Remarks: Typical value is based on specimen of 1.5mm AL\120um dielectric - 1 OZ Cu.

All the typical values listed above are for your reference only and not intended for specification. Please contact Boyu Technology CO.,LTD for detailed information.

Hatchi Industrial Zone Ruhu Town Huizhou City, Guangdong Province, China - TEL:0752-5317069 FAX : 0752-5317060 - [Http://www.boyu-global.com](http://www.boyu-global.com) - E-mail : sales@boyu-global.com